

中国认可 国际互认 检测 TESTING CNAS L6478



# **TEST REPORT**

:	WTF18F12134277C						
NN:LIV	Mid Ocean Brands B.V.						
JEX	7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong						
:	104438						
et :	Make-up mirror, Double sided compact mirror						
:-24	KC2204, KC2226, MO8767						
whi Intre Itek	<ol> <li>Determination of Lead content in the submitted sample in accordance with REACH regulation Annex XVII Entries 63 (EC) No. 1907/2006 and the amendment No. 836/2012 and (EU) 2015/628</li> <li>Determination of Cadmium content in the submitted sample in accordance with REACH regulation Annex XVII Entries 23 (EC) No. 1907/2006 and the amendment No. 552/2009, No. 494/2011, No. 835/2012 and (EU) 2016/217</li> <li>Nickel content requirement in Annex XVII Item 27 of the REACH Regulation (EC) No. 1907/2006 &amp; amendment No.552/2009 (formerly known as Directive 94/27/EC and 2004/96/EC)</li> </ol>						
211	Please refer to next page (s)						
NNLY	Please refer to next page (s)						
t	2018-12-28						
	2018-12-28 to 2019-01-09						
it.	2019-01-09						
:	Please refer to next page (s)						

#### Remarks:

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of reporter and reviewer.

Prepared By:

Waltek Services (Foshan) Co., Ltd. Address: No.13-19, 2/F., 2nd Building, Sunlink International Machinery City, Chencun, Shunde District, Foshan, Guangdong, China Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Compiled by:

Swing.Liang /Project Engineer

RVICES oprovec hang /Lab Manager



# Test Result:

# 1) Lead (Pb)

Test Method: With reference to IEC 62321-5:2013, the analysis was performed by ICP-OES.

Tool Hole	MDL		Results (mg/kg)		Limit (mg/kg)
Test Item	(mg/kg)	No.1	No.2	No.3	
Lead(Pb)	2	ND	ND ND	ND	500
Conclusion	- n	Pass	Pass	Pass	MILL THE

Tool Harry	MDL	su st	Results (mg/kg)	LIER MITE N	Limit
Test Item	(mg/kg)	No.4+No.5	No.6	No.7	(mg/kg)
Lead(Pb)	2	ND*	ND ND	ND	500
Conclusion	WIEL RITE	Pass V	Pass	Pass	

## Note:

(1) mg/kg = milligram per kilogram

(2) ND = Not Detected (lower than MDL)

(3) MDL = Method Detection Limit

- (4) Limit of Lead was quoted from REACH regulation Annex XVII Item 63 (EC) No. 1907/2006 and the amendment No. 836/2012 and (EU) 2015/628.
- (5) "\*" = As per applicant's requirement, the testing was conducted based on mixed components, the test result is for reference only

# 2) Cadmium (Cd)

Test Method: With reference to IEC 62321-5:2013, the analysis was performed by ICP-OES.

Test Item	MDL	Results (mg/kg)		
	(mg/kg)	No.4+No.5		
Cadmium(Cd)	2	ND*		
Conclusion	LET NITE WALT	Pass		

## Note:

- (1) mg/kg = milligram per kilogram
- (2) ND = Not Detected (lower than MDL)
- (3) MDL = Method Detection Limit
- (4) Limit of Cadmium according to REACH regulation Annex XVII Item 23 (EC) No. 1907/2006 and the amendment No. 552/2009, No. 494/2011 and No. 835/2012 and (EU) 2016/217.

Category	Limit (mg/kg)
Wet paint	100
Surface coating	1000
Plastic	100
Metal parts of jewellery and hair accessories	100

(5) "\*" = As per applicant's requirement, the testing was conducted based on mixed components, the test result is for reference only

Waltek Services (Foshan) Co.,Ltd. http://www.waltek.com.cn



# 3) Nickel release

Test method: With reference BS EN1811: 2011+A1:2015, Nickel content was determined by Inductively Coupled Argon Plasma Spectrometry

N <sup>N</sup>	Item No.	Sample Area (cm <sup>2</sup> )	Volume of Test	Nickel release (μg/cm²/week)				Conclusion
10	Area (cm )	Solution(ml)	Trial 1	Trial 2	Trial 3	Average	JITER NUT	
	No.1	35.72	- 35	ND S	ND	NDS	ND	Pass


#### Note:

- (1)  $\mu g/cm^2/week = microgram per square centimetre per week$
- (2) Method Detection limit =  $0.05 \,\mu g/cm^2/week$
- (3) ND = Not detected or less than the value of Method Detection Limit
- (4) Interpretation of test results:

* WALTER WALTER WALTE WALTE WALTE WALTE	Nickel Release(µg/cm²/week)			
Type of sample	Pass	Fail		
Other components in direct and prolonged contact with the skin	<0.88	≥0.88		
Post assemblies and body piercings (Post assemblies which are inserted into pierced parts of the human body)	<0.35	≥0.35		

## **Test Specimen Description:**

No.1: Silvery metal body No.2: Silvery metal body No.3: Silvery metal axle No.4: Black plastic shell No.5: Pink plastic shell No.6: Silvery glass mirror No.7: Black flocked bag





#### Sample photo:

80 90











#### Photographs of parts tested:








Waltek Services (Foshan) Co.,Ltd. http://www.waltek.com.cn

#### Reference No.: WTF18F12134277C

Page 7 of 7





=== End of Report ====

Waltek Services (Foshan) Co.,Ltd. http://www.waltek.com.cn