



中国认可  
国际互认  
检测  
TESTING  
CNAS L6478



# TEST REPORT

**Reference No.** ..... : WTF18F05112542C

**Applicant** ..... : Mid Ocean Brands B.V.

**Address** ..... : Unit 201 2/F., Laford Centre, 838 Lai Chi Kok Road, Cheung Sha Wan, Kowloon, Hong Kong.

**Manufacturer** ..... : 115253

**Sample Name** ..... : Double wall vacuum bottle

**Model No.** ..... : MO9431

**Test Requested** ..... : In accordance with Council of Europe Resolution AP(2004)5, Council of Europe Resolution CM/Res(2013)9 and Regulation (EC) No 1935/2004.

**Test Conclusion** ..... : **Pass** (Please refer to next pages for details)

**Date of Receipt sample** .... : 2018-05-23

**Date of Test** ..... : 2018-05-23 to 2018-05-29

**Date of Issue** ..... : 2018-05-29

**Test Result** ..... : Please refer to next page (s)

**Remarks:**

The results shown in this test report refer only to the sample(s) tested, this test report cannot be reproduced, except in full, without prior written permission of the company. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver.

**Prepared By:**

**Waltek Services (Foshan) Co., Ltd.**

Address: No. 13-19, 2/F, 2nd Building, Sunlink International Machinery City, Chencun Town, Shunde District, Foshan, Guangdong, China  
Tel :+86-757-23811398  
Fax:+86-757-23811381

Compiled by:

*Humour.Wu*

Humour.Wu / Project Engineer

Approved by:



*Dino Zhang*

Dino Zhang / Lab Manager

**Test Results:****1. Overall Migration Test**

Food Simulant	Test Condition	Result (mg/kg)	MDL(mg/kg)	Limit (mg/kg)
		No.1		
3% Acetic Acid	70°C for 6 hours	ND	20	60
50% Ethanol	70°C for 6 hours	ND	20	60

**Note:**

1. Test method: With reference to BS EN 1186-1: 2002, BS EN 1186-3: 2002 and BS EN 1186-9: 2002
2. "mg/kg" = milligram per kilogram of foodstuff in contact with
3. "°C" = Celsius degree
4. MDL= Method Detection Limit
5. ND = Not Detected, less than MDL
6. The specification was quoted from Council of Europe Resolution AP (2004)5.



# WALTEK

**2. Council of Europe Resolution CM/Res (2013)9-Specific Migration of Heavy Metal**

Test Items	1st+2nd Migration (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.2		
Aluminium (Al)	ND	0.2	35
Antimony (Sb)	ND	0.02	0.28
Chromium (Cr)	0.12	0.04	1.75
Cobalt (Co)	ND	0.02	0.14
Copper (Cu)	ND	0.2	28
Iron (Fe)	2.8	0.4	280
Manganese (Mn)	ND	0.2	12.6
Molybdenum (Mo)	ND	0.02	0.84
Nickel (Ni)	0.04	0.02	0.98
Silver (Ag)	ND	0.02	0.56
Tin (Sn)	ND	0.2	700
Vanadium (V)	ND	0.01	0.07
Zinc (Zn)	ND	0.2	35
Arsenic (As)	ND	0.002	0.014
Barium (Ba)	ND	0.2	8.4
Beryllium (Be)	ND	0.01	0.07
Cadmium (Cd)	ND	0.002	0.035
Lead (Pb)	ND	0.01	0.07
Lithium (Li)	ND	0.01	0.336
Mercury (Hg)	ND	0.002	0.021
Thallium (Tl)	ND	0.0002	0.0007
Magnesium (Mg)	ND	0.2	--
Titanium (Ti)	ND	0.02	--



Test Items	3rd Migration (mg/kg)	MDL (mg/kg)	Limit (mg/kg)
	No.2		
Aluminium (Al)	ND	0.1	5
Antimony (Sb)	ND	0.01	0.04
Chromium (Cr)	ND	0.02	0.25
Cobalt (Co)	ND	0.01	0.02
Copper (Cu)	ND	0.1	4
Iron (Fe)	ND	0.2	40
Manganese (Mn)	ND	0.1	1.8
Molybdenum (Mo)	ND	0.01	0.12
Nickel (Ni)	ND	0.01	0.14
Silver (Ag)	ND	0.01	0.08
Tin (Sn)	ND	0.1	100
Vanadium (V)	ND	0.005	0.01
Zinc (Zn)	ND	0.1	5
Arsenic (As)	ND	0.001	0.002
Barium (Ba)	ND	0.1	1.2
Beryllium (Be)	ND	0.005	0.01
Cadmium (Cd)	ND	0.001	0.005
Lead (Pb)	ND	0.005	0.01
Lithium (Li)	ND	0.005	0.048
Mercury (Hg)	ND	0.001	0.003
Thallium (Tl)	ND	0.0001	0.0001
Magnesium (Mg)	ND	0.1	--
Titanium (Ti)	ND	0.01	--

## Note:


1. Test Method: With reference to BS EN 13130-1: 2004, analysis was performed by ICP-OES and ICP-MS.
2. Test Condition and simulant: Sample(s) were migrated with 5g/L citric acid at 70°C for 6 hours.
3. "mg/kg" = milligram per kilogram of foodstuff in contact with
4. MDL = Method Detection Limit
5. ND = Not Detected, less than MDL
6. "--" = Not regulated
7. The specification was quoted from Technical Guide on Metals and alloys used in food contact materials of Council of Europe Resolution CM/Res (2013)9.



**Sample Photo:**




**Photograph of parts tested:**

No.	Photo of testing part	Parts Description	Client Claimed Material
1		Translucent silicone rubber	Silicone rubber



No.	Photo of testing part	Parts Description	Client Claimed Material
2		Silvery metal	Stainless steel

===== End of Report =====



# WALTEK